



PRO PLAN™ CG

2. MANUFACTURER

PROMA ADHESIVES Inc.

9801, Parkway, Anjou, Quebec Canada H1J 1P3
Tel.: 514.852.8585
Fax: 514.852.8225
Toll-free: 1 866.51.PROMA (77662)
Email: info@proma.ca
Web: www.proma.ca

3. PRODUCT DESCRIPTION

PRO PLAN™ CG is a commercial grade, fast-curing, polymer-modified, calcium aluminate cement-based self-leveling, self-drying and self-finishing underlayment that can be poured or pumped to correct, level and smooth substrates from 3 mm (1/8") up to 38 mm (1 1/2") deep.

Features

- Creates a smooth, level, and uniform surface
- Pour from 3 mm (1/8") up to 38 mm (1 1/2") in a single application
- FAST-SETTING: install ceramic tiles, porcelain or natural stones after 3 hours, and resilient floor covering, carpet, laminate flooring, engineered wood and wood parquet after 24 hours
- Mix only with water
- For use over concrete and exterior-grade plywood surfaces
- For interior institutional, commercial and residential applications
- Qualifies as part of PROMA's LIMITED WARRANTY PROGRAM up to a LIFETIME (contact PROMA for details)
- Compatible with all setting materials, adhesives, and floor coverings including wood parquet and rubber
- Use with uncoupling membranes (no primer required)
- Use with uncoupling membranes with underfloor heating systems (no primer required)
- Can be barrel mixed or pumped through most standard pumps (contact our technical department for pump compatibility)
- Can be used as a thermal mass over hydronic and electric radiant systems
- Can be applied over substrates up to 99% RH per ASTM F2170 (see LIMITATIONS)
- Super flow properties
- Blocks pH when installed greater than 5 mm (3/16") thick
- Will not promote mold, mildew or bacteria growth
- ZERO VOC



- Product characteristics improves indoor air quality compared to Portland cement-based products
- Eco friendly for users of the material
- Meets or exceeds ANSI A118.16 requirements
- Meets or exceeds compression and flatness requirements ASTM F710 (Standard Practice for Preparing Concrete Floors to receive Resilient Flooring)
- Meets or exceeds compression and flatness requirements ASTM F2873 (Standard Practice for the installation of Self-Leveling Underlayment, and the Preparation of Surfaces to Receive Resilient Flooring)
- Contributes to LEED® and WELL® objectives and requirements
- Intertek Clean Air GOLD Certified – conformance to California Department of Public Health (CDPH) Standard Method v1.2

Packaging

22.7 kg (50 lb) plastic bag



Concrete

Exterior-Grade
Plywood



Suitable Substrates

- ♦ Dry, completely cured concrete (at least 28 days old)*
- ♦ Cement backer units (CBU)*
- ♦ Gypsum and light-weight concrete surfaces**
- ♦ Existing ceramic and quarry tiles, porcelain, granite and marble†
- ♦ Cementitious and Epoxy Terrazzo floors†
- ♦ Exterior Grade Douglas Fir Plywood, certified CANPLY (SELECT) or (SEL-TF) CSA 121, for INTERIOR Residential Light-Duty Floors in dry areas only†
- ♦ Uncoupling membranes (no primer required)***
- ♦ Uncoupling membranes with underfloor heating systems (no primer required)**
- ♦ Metal such as steel, copper, stainless steel, aluminum or lead†
- ♦ Old cut-back adhesive **residue** and water-soluble adhesive **residues**†
- ♦ Existing VAT and VCT tiles, and non-cushioned vinyl sheet goods†
- ♦ Homogeneous PVC flooring†
- ♦ Resin-based floor coverings (epoxy, urethane or polyurethane)†

† When primed with PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C (see respective data sheet for details)

* Dry and very porous concrete must be primed with **DILUTED** PRO SUPERPRIME™ or PRO PRIME™ LP primer (see respective technical data sheet for details).

** Provided that the tensile bond strength of 72 psi (0.5 MPa) is reached as a minimum for self-leveling applications and when primed with PRO SUPERPRIME™ or PRO PRIME™ LP (see respective data sheet for details)

*** Consult manufacturer of uncoupling membrane, or uncoupling membrane with underfloor heating system, for specific installation method and recommendations.

Limitations

- ♦ For INTERIOR installations only.
- ♦ Do not use at temperatures below 10°C (50°F) or above 35°C (95°F).
- ♦ Do not use for applications exceeding 38 mm (1 1/2") in thickness. For installations exceeding 38 mm (1 1/2") in thickness, contact our technical department for proper recommendations.
- ♦ PRO PLAN™ CG can be applied over substrates up to 99% RH per ASTM F2170, provided any water intrusion, such as flooding, hydrostatic pressure, plumbing leaks, etc., is fully corrected. **NOTE: Moisture conditions must meet the requirements of all adhesives and finished flooring.** If they do not, a moisture mitigation membrane, such as PRO BLOCK™ MMS ECO, must be used (refer to the adhesive and finished flooring material technical documentation, or contact our technical department for details).
- ♦ When applying over new concrete, always test for curing compounds and sealers, which will impede bonding. If a sealer or curing compound is present, it must be mechanically removed before application.
- ♦ Do not mix with more water than recommended (see Mixing). Overwatering can lead to shrinkage, cracking, and reduced performance.
- ♦ PRO PLAN™ CG can be barrel mixed or pumped through most standard pumps (contact our technical department for pump compatibility).
- ♦ When pumping, follow the pump manufacturer's guidelines for maximum pumping distance and height. An excessively long hose or elevating the hose too high can cause material separation and reduced flow rates, resulting in a thicker output that may tempt users to overwater to compensate.
- ♦ Do not overmix. Excessive mixing, or moving the mixer up and down during mixing, will introduce air bubbles, leading to pinholing during application and curing.
- ♦ Do not apply directly over particleboard, chipboard, presswood, Lauan, masonite, OSB and other dimensionally unstable materials.
- ♦ Allow the self-leveling underlayment to dry properly prior to installing the floor covering.
- ♦ Do not leave without floor covering or exposed as a resurfacing material.
- ♦ When using a self-leveling product over a radiant heating system (previously checked for good functioning), turn the system off 24 hours prior to the installation and wait at least 2 weeks before turning it back on.
- ♦ Existing ceramic tiles, composite vinyl tiles, terrazzo, metal, epoxy-resin floors or old cut-back adhesives must be well prepared and primed with PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C prior to installing the self-leveling product (see respective technical data sheet).
- ♦ Do not use for filling cracks, holes and deep areas. Use PRO CEMIX™ or PRO CEMIX™ WS for those purposes (see respective technical data sheets for details).
- ♦ Do not use where high moisture and hydrostatic conditions and/or recurring moisture problems exist.
- ♦ Do not use in places subject to immersion.

- ♦ Do not add water to the mix once it begins to thicken.
- ♦ Do not add sand, aggregate or additional water to the mix.
- ♦ Protect the installation from excessive drafts through doors and windows, and from any direct air ventilation or heat radiation sources, such as direct sunlight, during and for at least 24 hours after the installation. These conditions could cause the self-leveling product to cure too quickly, resulting in micro-cracking.
- ♦ Protect stored material from high moisture and humidity, condensation, and rain.
- ♦ **Do not accelerate curing time by using ventilators or heating appliances.**

4. TECHNICAL DATA

Applicable Standards

NOTE: The technical data provided is averaged based on lab testing under controlled conditions (23° C [73° F] and 50% RH), done in accordance with standard industry testing methods (where applicable), and is subject to change without notice. Actual performance may vary depending on jobsite conditions and installation methods used. Please contact our technical services department for additional information.

PHYSICAL PROPERTIES (@23° C [73° F] and 50% RH)		
Property	ANSI A118.16 Requirements	Results
Working time		> 20 minutes
Flow time		> 20 minutes
Initial flow	> 110 mm (4.33")	≥ 130 mm (5.12")
Healing	≥ 10 minutes	≥ 18 minutes
Final set time	> 20 minutes	70 - 100 minutes
Time before installing Resilient floor covering		24 hours
Time before installing ceramic tile		3 hours
Time before for secondary applications of primer and self-leveling underlayment		24 hours

MECHANICAL PROPERTIES (@23° C [73° F] and 50% RH)		
Property	ANSI A118.16 Requirements	Results
Compression strength @ 4 hours	> 6.9 MPa (1,000 psi)	≥ 8.3 MPa (1,200 psi)
Compression strength @ 28 days	> 20.7 MPa (3,000 psi)	≥ 34.5 MPa (5,000 psi)
Tensile bond strength [Concrete] @ 24 hours	> 0.5 MPa (72.5 psi)	≥ 0.7 MPa (101.5 psi)
Tensile bond strength [Concrete] @ 7 days		≥ 2.2 MPa (319 psi)
Tensile bond strength [Concrete] @ 28 days	> 1.0 MPa (145 psi)	≥ 3 MPa (358 psi)
Flexural strength @ 28 days (ASTM C-348)		≥ 6.7 MPa (1,000 psi)
Wet density		2 g/mL
VOC content		0 g/L
Linear shrinkage (%) @ 28 days		< 0.04%
Shelf life		
12 months if kept in its original unopened packaging and stored in a dry location. Protect stored material from high moisture and humidity, condensation, and rain.		

Approximate coverage per 22.7 kg (50 lb) bag	
Thickness	Coverage
3 mm (1/8")	4.6 m² (50 ft²)
6 mm (1/4")	2.3 m² (25 ft²)
12 mm (1/2")	1.1 m² (12 ft²)
25 mm (1")	0.6 m² (6 ft²)
38 mm (1 1/2")	0.4 m² (4 ft²)





Surface Preparation

(Refer to PROMA Surface Preparation Guidelines for complete details)

Note: PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C can be used to ready nearly any surface for PROMA leveling underlayments without the need for scarifying or shotblasting, saving valuable time and money (see respective technical data sheet for details).

- ♦ All supporting surfaces must be structurally sound, solid and stable.
- ♦ Surfaces must be clean and free of dust, oil, grease, paint, tar, wax, curing agent, primer, sealer, form release agent or any deleterious substance and debris which may prevent or reduce adhesion.
- ♦ Acids, concentrated alkaline conditions and cleaning chemical residues must be neutralized or removed.
- ♦ All concrete substrates must be completely cured (at least 28 days old), solid, sound, slightly textured and have a direct tensile cohesive strength greater than 1.2 MPa (175 psi) when tested in accordance with ACI 503 R – (Appendix A) procedure.
- ♦ On grade or below grade concrete slabs must be installed over an effective vapor barrier.
- ♦ All concrete substrates must be dry and free of hydrostatic conditions and/or extreme moisture problems. Perform a calcium chloride moisture emission test (ASTM F-1869) on the concrete substrate before proceeding with the installation of the floor. Do not prime, repair, level or patch the substrate, or install any floor covering materials until moisture problems and conditions have been addressed to meet the requirements of the adhesives and finished flooring. **Please contact our Technical Service Department for appropriate recommendations.**
- ♦ When applying over new concrete, always test for curing compounds and sealers, which will impede bonding. If a sealer or curing compound is present, it must be mechanically removed before application.
- ♦ Existing Gypsum and light-weight concrete surfaces must have a minimum tensile bond strength of 72 psi (0.5 MPa) for self-leveling applications and be primed with PRO SUPERPRIME™ or PRO PRIME™ LP (see respective data sheet for details).
- ♦ Smooth concrete substrate surfaces must be either PRIMED with PRO SUPERPRIME™, PRO SUPERPRIME™ 1C, or PRO PRIME™ LP (undiluted) **OR** mechanically roughened in accordance with an engineer-approved procedure (shot-blasting, scarification, grinding, sand or water-blasting, etc.) to provide sufficient surface texture and profile for the adequate bonding of the subsequent leveling product. Then, **PRIMED** with **DILUTED** PRO SUPERPRIME or PRO PRIME LP primer (see respective technical data sheet for details)
- ♦ If concrete is dry and very porous, it must be **PRIMED** with PRO SUPERPRIME™ (diluted 1:3 with water) or PRO PRIME™ LP (diluted 1:3 with water) to prevent an uncontrolled absorption of water out of the self-leveling mix and also to avoid formation of air bubbles on the surface (see respective technical data sheet for details).
- ♦ Existing concrete slabs with old cutback adhesive or carpet adhesive **residues** must be scraped, roughened, cleaned, properly prepared and **PRIMED** prior to the application of the self-leveling underlayment. (Refer to the Surface Preparation Guidelines and PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C technical data sheet for full details or contact our Technical Service Department for appropriate recommendations).
- ♦ Wood substrates must be **PRIMED** with PRO SUPERPRIME™ (diluted 1:1 with water and powder), PRO SUPERPRIME™ 1C, or PRO PRIME™ LP (undiluted). Wood substrates must be solid and well-supported by joists spaced 400 mm (16") apart and should consist of two superimposed plywood sheet layers, each 16 mm (5/8") thick and set with a minimum of 3 mm (1/8") gap spacing between panels and 6mm (1/4") gapping along the perimeter walls, around columns, posts, drains and pipe openings. The top underlayment plywood layer must be fastened with non-oxidizing floor screws at every 15 cm (6") along panel edges and each way throughout the panel at 20 cm (8") centers. Floor surfaces along adjacent edges of panels must not be more than

0.75 mm (1/32") above or below each other. For ceramic and porcelain tiles up to 30 x 30 cm (12" x 12"), the structural design of the substrate must not allow a deflection greater than L/360 when tested to 136 kg (300 lb) concentrated loads in accordance with ASTM C627 Standard test method. For square and rectangular tiles with one edge dimension 38 cm (15") and 45 cm (18") up to 58 x 58 cm (23" x 23") the maximum deflection should not exceed L/540 unless an effective CIM (crack isolation membrane) is used in the installation system. **For tiles 60 x 60 cm (24" x 24") or larger and for ALL dimension stone installation, the maximum deflection must not exceed L/720. (Refer to ANSI A108. 01 requirements for Plywood sub-floors)**

- ♦ Existing ceramic tile, VCT or hard to bond to surfaces should be PROPERLY PREPARED, CLEANED and PRIMED with PROMA's PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C primer prior to the application of the self-leveling underlayment. (Refer to the Surface Preparation Guidelines and PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C technical data sheet for full details or contact our Technical Service Department for appropriate recommendations)

Notes: Scrape off as much as possible of the old cut-back adhesive.

Do not use sweeping compounds. This could leave an oily film on the concrete surface that will prevent a proper bond.

Mixing

Mixing ratio: 3 parts powder to 1 part water (by volume)

Manual Mixing

1. Use clean mixing tools and containers.
2. In a clean mixing container, measure and pour between 5.2 L to 5.68 L (1.4 US gal to 1.5 US gal / 5.5 US quarts to 6 US quarts) of cool, clean water per 22.7 kg (50lb) of PRO PLAN™ CG powder, while mixing slowly. **Do not use more water than recommended.** Overwatering can lead to shrinkage, cracking, and reduced performance.
3. Using a high-speed mechanical mixer (around 650 rpm) with an oval mixing paddle, mix until a smooth, lump-free, homogeneous consistency is achieved (about 2-3 minutes). **Do not overmix.** Excessive mixing, or moving the mixer up and down during mixing, will introduce air bubbles, leading to pinholing during application and curing.
4. The mixture is now ready for application.
5. Use the product within the shortest possible delay (within a few minutes).

Pump Mixing

Note: PRO PLAN™ CG can be pumped through most standard pumps designed for cement materials, provided they are in good working condition. Follow the pump manufacturer's instructions for use, or contact our technical department for compatibility, proper recommendations, and jobsite assistance.

- ♦ Use between 5.2 L to 5.68 L (1.4 to 1.5 US gal / 5.5 to 6 US quarts) of cool, clean water per 22.7 kg (50lb) bag of PRO PLAN™ CG powder.
- ♦ Prior to application, use the PROMA SELF-LEVELING FLOW TEST to ensure the product is properly mixed, homogeneous, and free of material separation. Fill the included flow ring and measure the product's spread on the target. The ideal flow for PRO PLAN™ CG is 14.5 – 15.5 cm (5.7" – 6.1").

PRO SUPERPRIME™

PROMA has engineered a revolutionary primer that can ready nearly any surface for PROMA leveling underlayments without the need for scarifying or shotblasting. Use PRO SUPERPRIME™ or PRO SUPERPRIME™ 1C with PRO PLAN™ CG as an unbeatable system for preparing a substrate for flooring installation. Surface must meet a minimum of 0.5 MPa (72 psi) tensile bond strength. In areas subject to heavy traffic, a minimum of 1.2 MPa (175 psi) tensile bond strength is required (see respective technical data sheet for details).





Application

Application Items Needed:

- ♦ Gloves and safety glasses
- ♦ Spiked shoes
- ♦ Spiked roller
- ♦ Gauge rake
- ♦ Smoother

Note: Use PRO LEVEL PEGS™ with a laser level to help ensure precise and consistent depth of the material.

Application Instructions:

1. Quickly pour or pump the self-leveling mixture onto the substrate. Apply enough material so that higher areas are adequately covered.
2. Spread mixture using a spiked roller or gauge rake to set it in place to the desired thickness.
3. Smooth the surface of the product using a smoother.

IMPORTANT NOTES:

Pumping: Follow the manufacturer's guidelines for maximum hose length and height. Excessively long hoses or elevating the hose too high can cause material separation and reduced flow rates, resulting in a thicker output that may tempt users to overwater to compensate. Additionally, regularly verify that the flow remains steady and uniform.

Installation of a Second Layer: Apply a second layer only after the material has cured to a walkable level of hardness. Prime the surface using PRO SUPERPRIME™, PRO SUPERPRIME™ 1C, or PRO PRIME™ LP (diluted) prior to application. (See respective technical data sheet for details or contact our Technical Service Department for appropriate recommendations.)

Uncoupling Membranes with an Underfloor Heating System: Certain manufacturers allow the installation of alternative flooring (other than tile) by creating a thermal mass with a self-leveling product, such as PRO PLAN™ CG. The thermal mass must be between 6 and 12 mm (1/4" to 1/2"); refer to the heating system manufacturer's technical data sheet for additional information. For projects greater than 23 m² (250 sq. ft.), please contact our technical department for proper recommendations.

Cracking: Some slight, variable cracks may occur due to substrate movement, minor shrinkage, and around obstructions such as sharp wall angles. This is normal for a cementitious product. However, if during curing there are excessive drafts through doors and windows, direct air ventilation, or heat radiation sources, such as direct sunlight, these conditions can cause the self-leveling product to cure too quickly, resulting in micro-cracking. **Do not attempt to accelerate drying and curing through forced ventilation, fans, or heat-blowers.**

Expansion and Control Joints

All expansion and control joints must be carried through from the substrate to the final flooring and filled with an industry-approved flexible sealant. Do not fill or cover expansion and control joints with installation material. Contact PROMA's technical department for additional information.

Curing and Protection

- ♦ Do not use a damp-curing method or curing and sealing compounds.
- ♦ Protect from foot traffic for at least 3 hours.
- ♦ Install ceramic tiles, porcelain or natural stones after 3 hours.
- ♦ Install resilient floor covering, carpet, engineered wood and wood parquet after 24 hours.
- ♦ Material should be completely dry prior to applying the floor covering adhesive.

Note: Drying time may vary depending on the temperature and humidity level. **Do not attempt to accelerate drying and curing through forced ventilation, fans or heat-blowers.**

- ♦ Protect from traffic and dust until floor covering is completely installed.
- ♦ Protect from heavy loads (such as forklifts) for at least 72 hours.

Cleaning

Clean tools and hands with water while the product is still fresh.

Health and Safety

Refer to the Safety Data Sheet (SDS) for complete details.

6. AVAILABILITY AND COST

PROMA products are widely available in Canada and the Northeast United States. To find a distributor of PROMA products, call **toll-free: 1.866.51.PROMA (77662)**.

7. WARRANTY

PROMA warrants that this product is manufactured using quality raw materials and is of merchantable quality and suitable for the purpose for which it was intended. PROMA's liability under this warranty shall be limited to the replacement of its product proven to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising from the use of/or the inability to use this product.

PRO PLAN™ CG qualifies as part of PROMA's LIMITED WARRANTY PROGRAM up to a LIFETIME, the whole subject to the terms and conditions of the applicable warranty program. This limited program applies to specific individual PROMA products when used together as a complete system. A combination of qualifying PROMA products must be properly used for each stage of preparation, installation, and finishing to be eligible for this limited warranty program. Visit www.proma.ca, or contact PROMA by phone (toll-free: 1 866.51.PROMA [77662]) or by email (info@proma.ca) for complete terms and conditions.

8. MAINTENANCE

Product requires no special maintenance. Do not leave without floor covering or exposed as a resurfacing material.

9. TECHNICAL SERVICE

For more detailed information on this product, please contact our technical department for proper recommendations and job field assistance. **Toll-free: 1.866.51.PROMA (77662).**

10. FILING SYSTEM

Additional information is available upon request, or by visiting www.proma.ca.

PROMA Adhesives Inc.

9801, Parkway, Anjou, Quebec Canada H1J 1P3

Tel.: 514.852.8585

Fax: 514.852.8225

Toll-free: 1 866.51.PROMA (77662)

Email: info@proma.ca

© 2026 PROMA Adhesives, Inc.